



® TECHNICAL DATA SHEET (TDS)

KTH 200°C HEAT RESISTANT ALUMINIUM PAINT

Product Description

KTH 200°C HEAT RESISTANT ALUMINIUM PAINT is single component solvent based heat resistance aluminium paint. It is formulated with modified silicone resin and has atmospheric dry heat resistant up to 150°C, with occasional peak temperature up to 200°C. It gives silvery and low gloss finishing to painted surfaces.

Uses

As primer, mid coat or top coat in a multi-coat coating system. Most suitable for use on properly prepared steel surfaces.

Composition

Pigment : Aluminium paste.
Binder : Silicone resin
Solvent : Hydrocarbon

Physical Characteristics of the Paint:

Density : 0.96 – 1.02
Volume Solid : 35 ± 5%
Viscosity : 45 ± 5 KU at 30°C
Theoretical Coverage : 10 – 13 m²/litre
Colour : Aluminium

Coating Properties:

Recommended Dry Film Thickness	: 25 - 35 microns per coat
Recommended Wet Film Thickness	: 70 - 100 microns per coat
Recommended Coating System	: HR 200°C / HR 200 °C
Recommended Numbers of coat	: One to two
Drying Time	: Touch Dry – 15 mins, Dry to handle – 1 hour
Recoating interval	: At least 8 hours
Curing Time	: 1 day

Surface Preparation:

Previous painted surface and bare substrate must be completely dry and free from rust, mill-scale, dirt, grease and other contaminants before painting. For maximum adhesion and durability of paint performance, all bare surfaces should be prepared by meant of sand blasting, power tools, hand tools and etc.

Application Method:

Method of Application	: Brush, roller, and spray application.
Product Preparation	: Stir mixture thoroughly before use. No thinning is required. However, 10% of thinner can be added for workability.
Pot Life (at 30°C)	: No pot life limit.

Safety Precaution:

1. This product is flammable.
2. Keep away from sources of ignition.
3. Keep container tightly closed and keep out of reach of children.
4. Wear suitable personal protective clothing during painting.
5. Ensure adequate ventilation. Do not breathe or inhale spray mist.
6. Do not apply when the relative humidity exceeds 85%.
7. Avoid skin and eye contact. Spillage on skin should be removed immediately with cleanser, soap and water. Eye should be well flushed with water and seek medical advice immediately if discomfort persists.